

EA440EB-0.0A~-0.8
(ステンレスシム)

サイズ 150mmX1.25m

品番	厚さ(mm)	許容差(mm)	重量(g)
EB-0.0A	0.05	±0.006	112
EB-0.1	0.1	±0.012	193
EB-0.1A	0.15	±0.018	283
EB-0.2	0.2	±0.024	360
EB-0.2A	0.25	±0.030	441
EB-0.3	0.3	±0.060	558
EB-0.4	0.4	±0.045	688
EB-0.5	0.5	±0.047	990
EB-0.6	0.65	±0.054	1233
EB-0.8	0.8	±0.064	1431

- (参考)
- a full hard, cold rolled, Type 302
 - Rockwell Hardness: C40-45
 - Ultimate Tensile Strength: 185,000p.s.i. Min.
(p.s.i.=0.0703kgf/cm²)
(1Mpa=10.2kgf/cm²)

TYPICAL ANALYSIS

C .15max	Si .75max
Mn 2.00max	Ni 8.00-10.00
P .045max	Cr 17.00-19.00
S .030max	N .10max