

EA440EC-0.0A~-0.8
(ブラスシム)

サイズ 150mmX2.5m

品番	厚さ(mm)	許容差(mm)	重量(g)
EC-0.0A	0.05	±0.006	207
EC-0.1	0.1	±0.01	369
EC-0.1A	0.15	±0.013	544
EC-0.2	0.2	±0.019	706
EC-0.2A	0.25	±0.025	882
EC-0.3	0.3	±0.026	1098
EC-0.4	0.4	±0.045	1386
EC-0.5	0.5	±0.045	1651
EC-0.6	0.65	±0.066	2286
EC-0.8	0.8	±0.066	2758

(参考) ・a half hard, cold rolled, CDA 260alloy
・Rockwell Hardness: 30T 50-68
・Tensile Strength: 57-67,000p.s.i.
(p.s.i.=0.0703kgf/cm²)
(1Mpa=10.2kgf/cm²)

Elongation :23% in 2"

TYPICAL ANALYSIS
Cu 70%-Zn 30%